

Special Stainless

IMPHY 25-9-4

IMPHY 25-9-4 is a high alloy duplex stainless steel (austenitic-ferritic) which shows :

- > Outstanding resistance to a wide range of highly corrosive media under oxidizing and reducing conditions.
- > High resistance to erosion corrosion and corrosion fatigue.
- > Excellent resistance to pitting and crevice corrosion and to stress corrosion cracking in chloride environment.
- > Very high mechanical strength.

Chemical composition

C	Cr	Ni	Mo	Mn	Si	P	S	N	Cu	W
0.03	24 27	8 10.5	2.5 4.5	2.5	1	< 0.03	< 0.02	0.2 0.3	1.5	1

International standards

AWS A5.9 ER2594 ; EN 12072: 25 9 4 L

Typical applications

Welding of plates, sheets, and tubes in the chemical and petrochemical process industry (chloride environment), in the pulp and paper industry, pollution control equipment for environmental protection.

Mechanical properties

		Tensile strength (MPa)	Elongation %
Hot rolled and pickled condition	Delivery condition at 20°C	< 1000	10 - 35

Welding

IMPHY 25-9-4 is used for welding of duplex and super-austenitic stainless steels.

IMPHY 25-9-4 is useful for the surfacing of wide range of steels in particularly aggressive environments.

Available Forms

IMPHY 25-9-4 is delivered in wire.

©June 2020, Aperam Alloys Imphy

The data enclosed in this document are given as indicative values and correspond to our standard product.

Different specific requirements are subject to discussion and formal approval by Aperam Alloys Imphy. For further information or special request, please contact us.

IMPHY® is a registered trademark of Aperam Alloys Imphy



www.aperam.com
nickel.alloys@aperam.com



Aperam Alloys Imphy
 B.P. 1
 Avenue Jean Jaurès
 F- 58160 Imphy