

Cold Rolled Strip



1. Description, standards & chemical

PERMIMPHY SP is nickel-iron soft magnetic alloy used for the manufacture of stator watch motors

International standards

ASTM A 753, DIN 17405, IEC 404, JIS C 2531

Chemical composition (%weight)

	Ni	Mo	Fe
Typical value	80	5	Bal

2. Physical properties

Density (g/cm ³)	Melting T° (°C - °F)	Curie T° (°C - °F)	Thermal expansion (10 ⁻⁶ .°K ⁻¹)	Resistivity (μΩcm)	Thermal conduction (W/°Km)	Specific heat (J.Kg ⁻¹ .°K ⁻¹)
8.7	1450 - 2642	420 - 788	12	60	19	460

3. Magnetic properties *

Conditions	Thickness (mm - ")	Saturation induction (G - T at 1 Oe ≈ 80 A/m)	Coercive force (Oe - A/m)	Permeability (at 5 mOe ≈ 0.4 A/m)
DC	0.34 - 0.0134	7500 - 0.75	0.005 - 0.4	520000

* Typical values measured on rings sample th. 0.34mm / 0.0134" after heat treatment at 1170°C / 2138°F in pure & dry Hydrogen after proper cooling

4. Mechanical properties *

Temper	Hardness (HV)	Grain size	Tensile strength (MPa - KSI)	Yield strength (MPa - KSI)	Elongation (%)	Young's modulus (MPa - KSI)
Hard	320	-	1050 - 152	1030 - 149	3	230000 - 33350

* Typical values for material to be tested in accordance with NF EN 10002, NF EN ISO 6507, NFA 04102

5. Standard Delivery & dimensions available

Form *	Thickness(mm / ")	Width (mm / ")	Length (mm / ")	Temper
Coil	0.40 to 0.70 / .0157 to .0275	10 to 640 / .4 to 25.2	-	Hard

* Depending on thickness, width & temper

The data enclosed in this document are only given as indicative values and correspond to our standard product. Different specific requirements are subject to discussion and formal approval by Aperam Alloys Imphy. For further information or special request, please contact us.